

Environmental Product Declaration



A Cradle-to-Gate EPD of Sawn Round Timber Framing Products (SRT)





According to
ISO 21930
ISO 14025
ISO 14040/44



Summary Results –per m ³ Full Results in Table 1		Cradle-to-Gate Total
Global Warming Potential	kg CO ₂ e	1.79E+02
Depletion potential of the stratospheric ozone layer	kg CFC11e	1.76E+02
Acidification potential of soil and water sources	kg SO ₂ e	6.77E-01
Eutrophication potential	kg Ne	2.75E-01
Formation potential of tropospheric ozone	kg O ₃ e	8.67E-07
Abiotic depletion potential (ADPfossil) for fossil resources	MJ, NCV	2.80E+03

1.0 General Information

EPD Program and Program Operator	ASTM International 100 Barr Harbor Drive PO Box C700 West Conshohocken, PA, 19428-2959 USA www.astm.org  ASTM INTERNATIONAL Helping our world work better
General Program Instructions and Version Number	ASTM Program Operator for Product Category Rules (PCR) and Environmental Product Declarations (EPDs) - General Program Instructions, version: 6.0
Manufacturer	National Association of homebuilders National Housing Center 1201 15th Street, NW Washington, DC 20005 https://nwfa.org 
Declaration Number	EPD 999
Declared Product	Sawn Round Timber Framing Products (SRT)
Declared Unit	1 m ³ of SRT produced.
Reference PCR and Version Number	ISO 21930:2017 Sustainability in Building Construction — Environmental Declaration of Building Products. [7] ISO 14040/44:2006 Underwriters Laboratory, Product Category Rule for Architectural and Structural Wood Products. Version 1.1. (2020)
Markets of Applicability	Construction Sector, Building homes
Date of Issue	25.09.2025
Period of Validity	24.09.2030
EPD Type	Industry Average EPD

EPD Scope	Cradle-to-Gate		
Year of reported manufacturer primary data	2019		
LCA Software	SimaPro v9.2		
LCI Databases	USLCI [9], Ecoinvent 3.9 [15], Datasmart 2023[8]		
LCIA Methodology	TRACI 2.1 [3]		
The sub-category PCR review was conducted by:	Jack Geibig, Chair Ecoform	Dr. Thomas Gloria Industrial Ecology Consultants	Thaddeus Owen
LCA and EPD Developer This life cycle assessment was conducted in accordance with ISO 14044 and the reference PCR by:	<div><div><div>Athena Sustainable Materials Institute</div><div>100 Broadview Avenue, Suite 909 Ottawa, ON K1S 5P6</div><div> Athena Sustainable Materials Institute</div></div><div>https://www.athenasmi.org/ Athena</div></div>		
<div><div><div>This declaration was independently verified in accordance with ISO 14025:2006[4]. Environmental declarations from different programs (ISO 14025) may not be comparable.</div><div>The UL Environment “Part A: Calculation Rules for the Life Cycle Assessment and Requirements on the Project Report,” v3.2 (September 2018), based on ISO 21930:2017 and CEN Norm EN 15804 (2012), serves as the core PCR, with additional considerations from the USGBC/UL Environment Part A Enhancement (2017).</div><div><div><input type="checkbox"/> INTERNAL</div><div><input checked="" type="checkbox"/> EXTERNAL</div></div></div></div>			
Independent Verifier This life cycle assessment was independently verified in accordance with ISO 14044 [6] and the reference PCR by:	<div><div><div>Tim Brooke</div><div>100 Barr Harbor Drive PO Box C700 West Conshohocken, PA, 19428-2959 USA</div><div>www.astm.org</div></div></div>		
LCA and EPD Manufacturer Participants			
			

About the National Wood Flooring Association

NAHB collaborates with industry partners to quantify and report the environmental impact of building materials and products. For example, in the LCA report you shared, NAHB commissioned the Athena Sustainable Materials Institute to conduct a cradle-to-gate LCA of log home and timber frame products. The study was aligned with the association’s goal of promoting sustainable building practices and creating transparency in environmental impacts across the construction sector. Through such initiatives, the NAHB supports efforts toward more sustainable construction practices by providing detailed data on environmental performance to industry stakeholders, including architects, policymakers, and manufacturers. This EPD initiative helps builders meet criteria for sustainable building certifications like LEED and Green Globes, advancing environmentally friendly construction practices in North America. Detailed information about NAHB can be found at <https://www.nahb.org/>

2. PRODUCT DESCRIPTION

Sawn Round Timber Framing Products (SRT)

Sawn Round Timber framing products are structural components crafted from round logs that are partially processed to retain their natural strength while providing a more uniform appearance for framing applications. These timber products offer excellent load-bearing capacity and much more economically friendly than any laminated products in the market. Also, timber products are far better than laminated products in terms of carbon footprint which improves the environmental performance of the product. These logs offer exceptional structural integrity, combining the natural beauty of wood with enhanced precision for construction projects requiring stability and aesthetics.

SRT Product Variations

Full conformance with the PCR for wood products allows EPD comparability only when all life cycle stages (A1 to C4 and beyond, if applicable) have been considered, when EPDs comply with all referenced standards, utilize the same sub-category Part B PCR, and apply equivalent scenarios related to the construction works. It is important to note that variations and deviations may still occur.

Sawn Round Timber framing products vary based on wood type, size, and finishing options to meet diverse project requirements. Key variations include:

- **Log Diameter:** Available in multiple sizes, ranging from smaller to larger diameters for different structural needs.
- **Species:** Made from both softwood and hardwood, selected for their strength and suitability for framing.
- **Surface Finish:** Available in natural, smooth-planed, or lightly sanded finishes to match project aesthetics.
- **End Treatments:** Can include standard square ends or customized profiles for precise jointing and framing requirements.

Source of Timber and Sustainability

The logs used for producing SRT products are sourced from sustainably managed forests across North America. Timber selection and processing follow sustainable forestry practices to ensure environmental stewardship, with a focus on minimizing the ecological footprint. Key highlights include:

- **Sustainable Growth:** Timber harvesting is aligned with responsible forestry, ensuring the growth of more trees than are removed annually.
- **Selective Harvesting:** Practices such as selective logging help protect forest ecosystems, ensuring long-term forest health and regeneration.
- **Common Species:** Typical species used include pine, spruce, fir, and oak, known for their strength, stability, and suitability for structural applications.

3. METHODOLOGY

The underlying LCA investigates the lifecycle stages of Sawn Round Timber Framing Products production in the United States and Canada from cradle-to-gate.

System Boundaries and Product Flow Diagram

The scope for Sawn Round Timber (SRT) products follows a cradle-to-gate system boundary, covering environmental impacts from raw material extraction to the product ready for shipment. It consists of three modules: A1 – Raw Material Production, which includes log harvesting, reforestation, thinning, nursery operations, fertilization, and preparation of secondary materials; A2 – Raw Material Transportation, detailing the movement of logs and inputs to manufacturing sites via trucks, rail, or ships; and A3 – Manufacturing, which involves milling logs to precise dimensions, applying finishes, and packaging the products for delivery. The manufacturing process uses electricity, propane, and wood fuels, along with consumables like motor oil and hydraulic fluids, while generating co-products

like wood chips and shavings, which are reused for energy or sold to other industries. This cradle-to-gate approach ensures a comprehensive and transparent assessment of the environmental impacts of SRT products, supporting sustainable building practices and environmentally responsible decision-making.

Building Life Cycle Information Modules																
Production stage			Construction Stage		Use stage							End-of-life stage				Substitution Effects
Extraction and upstream production	Transport to factory	Manufacturing	Transport to site	Installation	Use	Maintenance	Repair	Replacement	Refurbishment	Operational Energy Use	Operational Water Use	De-Construction/ Demolition	Transport to waste	Waste processing	Disposal	Benefits Outside System
A1	A2	A3	A4	A5	B1	B2	B3	B4	B5	B6	B7	C1	C2	C3	C4	D
X	X	X

Figure 2: Life Cycle Stages and Information Modules per ISO 21930:2017

Construction and Service Life Assumptions

The construction and service life assumption aligns with typical building industry standards. While the report emphasizes the cradle-to-gate scope, meaning that the product's full lifecycle (including end-of-life) is not assessed here, the data suggests that SRT products have a long service life, contributing to their sustainability performance.

Declared Unit

The declared unit for the SRT product is defined as one cubic meter (1 m³) of sawn round timber framing. This unit provides a consistent basis for measuring the product's environmental impact across different stages of production. The SRT product system primarily consists of wood with a density of 439.8 dry kg/m³.

Data Sources

The data sources for this study include both primary data collected directly from eight manufacturing facilities across North America and secondary data from publicly available databases such as DATASMART 2023 and Ecoinvent 3.9. Primary data reflects facility-specific information on energy use, material inputs, and manufacturing processes for the 2021 production year. Secondary data covers aspects such as transportation and raw material extraction.

Treatment of Biogenic Carbon

The report follows the guidelines of UL PCR Part B and ISO 21930 to account for biogenic carbon. North American forests are assumed to have a neutral forest carbon stock, meaning that the biogenic CO₂ emitted during biomass combustion (e.g., for kiln-drying) does not contribute to the overall global warming potential. Although the cradle-to-gate scope of this study does not cover end-of-life emissions, the biogenic carbon stored in the product is quantified as 806.31 kg CO₂ equivalent per m³ (assuming 50% carbon content). This ensures that the carbon sequestration within the wood product is transparently reported and can be used in future cradle-to-grave assessments. Biogenic carbon emissions and removals are reported in accordance with ISO 21930 7.2.7. and 7.2.12. Detailed information is provided in Section 4 of the underlying LCA.

Allocation Procedures:

Allocation procedures are conducted in accordance with ISO 14044 and ISO 21930. When processes produce multiple co-products, inputs and outputs are allocated to the products based on physical relationships (such as mass or energy content) or economic value, depending on data availability and relevance. When neither physical nor economic allocation is possible, system expansion is applied to avoid allocation. Specific allocation details for coproducts are provided within the life cycle inventory documentation.

Cut-off Criteria:

The cut-off criteria applied in this study exclude flows that collectively contribute less than 1% of the total mass, energy, or environmental significance of the product system. All significant inputs and outputs are included. No known flows are deliberately excluded from this EPD.

Health, Safety and Environmental Aspects

This product does not contain hazardous, dangerous, or regulated substances that are known to adversely affect human health or the environment. The product is free from substances that are restricted or subject to specific regulations under applicable health, safety, and environmental legislation. This declaration is made in accordance with ISO 21930:2017 standards for sustainability in building construction.

4. LCA Results

The Life Cycle Assessment (LCA) results for SRT products provide a detailed environmental profile from cradle-to-gate. The impact categories and characterization factors are based on the U.S. EPA's TRACI 2.1 methodology. The LCA modeling uses SimaPro v9.1 to gather life cycle inventory (LCI) data and calculate the life cycle impact assessment (LCIA) results.

The contribution analysis shows that manufacturing (A3) is the most significant phase, contributing 65.4% to the Global Warming Potential (GWP), followed by raw material production (A1) at 18.9% and transportation (A2) at 15.7%. The effective use of renewable energy and co-products, such as wood chips, aligns the process with sustainable practices. These results offer transparency into the environmental performance of SRT products, promoting the adoption of carbon-storing building materials in sustainable construction projects.

Table 1: LCIA Results Summary for Cradle-to-Gate production of 1 m³ of SRT-absolute basis

Core Mandatory Impact Indicator	Unit	Total	A1	A2	A3
Global warming potential –w/ biogenic CO ₂	kg CO ₂ e	1.82E+02	-9.26E+02	2.81E+01	1.08E+03
Global warming potential – TRACI 2.1	kg CO ₂ e	1.79E+02	3.35E+01	2.80E+01	1.18E+02
Depletion potential of the stratospheric ozone layer	kg CFC11e	1.76E+02	3.33E+01	2.77E+01	1.15E+02
Acidification potential of soil and water sources	kg SO ₂ e	6.77E-01	3.04E-01	1.53E-01	2.20E-01
Eutrophication potential	kg Ne	2.75E-01	3.02E-02	1.23E-02	2.32E-01
Formation potential of tropospheric ozone	kg O ₃ e	8.67E-07	1.51E-09	4.88E-08	8.16E-07
Abiotic depletion potential (ADP _{fossil}) for fossil resources	MJ, NCV	1.39E+01	6.13E+00	4.42E+00	3.34E+00
Use of Primary Resources					
Renewable primary energy carrier used as energy	MJ, NCV	8.89E+01	0.00E+00	6.38E-01	8.82E+01
Renewable primary energy carrier used as material	MJ, NCV	1.08E+04	1.08E+04	0.00E+00	0.00E+00
Non-renewable primary energy carrier used as energy	MJ, NCV	2.80E+03	4.53E+02	3.52E+02	1.99E+03

Non-renewable primary energy carrier used as material	MJ, NCV	0.00E+00	0.00E+00	0.00E+00	0.00E+00
Secondary Material, Secondary Fuel, and Recovered Energy					
Secondary material	kg	0.00E+00	0.00E+00	0.00E+00	0.00E+00
Renewable secondary fuel	MJ, NCV	0.00E+00	0.00E+00	0.00E+00	0.00E+00
Non-renewable secondary fuel	MJ, NCV	0.00E+00	0.00E+00	0.00E+00	0.00E+00
Recovered energy	MJ, NCV	0.00E+00	0.00E+00	0.00E+00	0.00E+00
Mandatory Inventory Parameters					
Consumption of freshwater resources	m ³	4.99E+00	3.50E-02	4.57E+00	3.87E-01
Indicators Describing Waste					
Hazardous waste disposed	kg	3.99E-02	0.00E+00	4.14E-04	3.95E-02
Non-hazardous waste disposed	kg	6.56E+00	2.17E+00	4.86E-01	3.91E+00
High-level radioactive waste	m ³	2.33E-07	0.00E+00	2.75E-09	2.30E-07
Intermediate- and low-level radioactive waste	m ³	2.06E-06	0.00E+00	1.32E-08	2.04E-06
Components for re-use	kg	0.00E+00	0.00E+00	0.00E+00	0.00E+00
Materials for recycling	kg	0.00E+00	0.00E+00	0.00E+00	0.00E+00
Materials for energy recovery	kg	0.00E+00	0.00E+00	0.00E+00	0.00E+00
Recovered energy exported from the product system	MJ, NCV	0.00E+00	0.00E+00	0.00E+00	0.00E+00
Additional Inventory Parameters					
Biogenic Carbon Removal from Product	kg CO ₂	-9.96E+02	-9.96E+02	0.00E+00	0.00E+00
Biogenic Carbon Emission from Product	kg CO ₂	8.27E+02	0.00E+00	0.00E+00	8.27E+02
Biogenic Carbon Removal from Packaging	kg CO ₂	-5.76E-01	-5.76E-01	0.00E+00	0.00E+00
Biogenic Carbon Emission from Packaging	kg CO ₂	5.76E-01	0.00E+00	0.00E+00	5.76E-01
Biogenic Carbon Emission from Combustion of Waste from Renewable Sources Used in Production	kg CO ₂	0.00E+00	0.00E+00	0.00E+00	0.00E+00

5. LIMITATIONS

Comparability

The study does not include comparative assertions, making it challenging to benchmark SRT products against other building materials. Differences in system boundaries, allocation methods, and data sources would need to be harmonized for meaningful comparisons, limiting the applicability of the results for competitive product evaluations or market-based comparisons. Environmental declarations from different programs (ISO 14025) may not be comparable. Comparison of the environmental performance of wood products using EPD information shall be based on the product's use and impacts at the construction works level, and therefore EPDs may not be used for comparability purposes when not considering the construction works energy use phase as instructed under this PCR".

Forest Management

The study assumes that North American forests are carbon neutral, meaning there is no net carbon loss due to sustainable forestry practices. However, this assumption may not fully account for regional variations in forest management, changes in land use, or unforeseen environmental events. These factors could affect the actual carbon balance and introduce uncertainty regarding the long-term sustainability of biogenic carbon sequestration.

While this EPD does not address landscape level forest management impacts, potential impacts may be addressed through requirements put forth in regional regulatory frameworks, ASTM 7612-15 guidance, and ISO 21930 Section 7.2.11 including notes therein. These documents, combined with this EPD, may provide a more complete picture of the environmental and social performance of wood products.

EPD Scope

The cradle-to-gate scope limits the EPD by excluding the product's use phase, maintenance, and end-of-life stages. This restricts the report's ability to offer insights into the total environmental performance of SRT products in real-world applications.

Accuracy of Results

The accuracy of the results may be affected by the limited sample size, as only eight manufacturing facilities were included. Additionally, the reliance on secondary data for aspects such as transportation and raw material extraction introduces variability. While primary data collection reflects actual production practices, averaging across facilities could mask specific differences, reducing the precision of the environmental impact assessments for individual production sites.

6. REFERENCES

1. Abergel, T.; Dean, B.; Dulac, J. 2017. Towards a zeroemission, efficient, and resilient buildings and construction sector: Global Status Report 2017. Paris, France: UN Environment, International Energy Agency.
2. ULE. 2018. Part A: life cycle assessment calculation rules and report requirements. Washington, DC: UL Environment. 47 p.
3. ULE. 2019. Guidance for building-related products and services: Part b: Structural and architectural wood products EPD requirements. Washington, DC: UL Environment. 31 p.
4. ISO. 2006c. ISO 14044. Environmental management: life cycle assessments: requirements and guidelines. Geneva, Switzerland: International Standardization Organization. 54 p.
5. ISO. 2006b. ISO 14040. Environmental management: life cycle assessment; principles and framework. Geneva, Switzerland: International Organization for Standardization. 28 p.
6. PRé Consultants. 2020. SimaPro 9.5 life-cycle assessment software package, version 9.0. Amersfoort, the Netherlands: PRé Consultants.
7. LTS. 2023. DATASMART LCI package (US-EI SimaPro®Library). Huntington, VT: Long Trail Sustainability. <https://ltsexperts.com/services/software/datasmart-lifecycle-inventory/>.
8. Bare, J. 2011. TRACI 2.1: the tool for the reduction and assessment of chemical and other environmental impacts 2.1. Clean Technologies and Environmental Policy. 13(5): 687-696.
9. ISO. 2017. ISO 21930. Sustainability in buildings and civil engineering works — Core rules for environmental product declarations of construction products and services. Geneva, Switzerland: International Standardization Organization. 90 p.
10. ASTM International. 2022. General Program Instructions for EPDs, Version 8.0. ASTM International, West Conshohocken, PA.